

TEXAS-JACK™ RG



Liquid Crumb Rubber Roof Coating



PRODUCT DESCRIPTION:

TEXAS-JACK™ RG is an elastomeric copolymer rubber based liquid with rubber granules incorporated to provide texture and slip resistance. The modified formulation has excellent elongation, UV resistance and weathering characteristics. This flexible textured membrane also has excellent resistance to ozone as well as low temperature flexibility. TEXAS-JACK RG has displayed good adhesion to many properly prepared substrates including EPDM.

RECOMMENDED FOR:

Most common roof substrates such as concrete, wood, metal, EPDM, APP, TPO, and Hypalon

SOLIDS BY WEIGHT:

69% (+,-3)

SOLIDS BY VOLUME:

62% (+,-3)

RECOMMENDED COVERAGE:

Coverage depends on surface conditions and application procedures. Normally, 1 gallon per 17.5 square feet provides the correct coverage thickness.

COLORS:

Standard: shadow gray. Many other colors are available upon request. Colors may vary from batch to batch due to variations in feed stock material.

RECOMMENDED FILM THICKNESS:

56 mils total dry film thickness will result from applying the recommended 90 mils wet thickness.

COVERAGE PER GALLON:

133-267 square feet per gallon @ 6-12 mils

PACKAGING:

Available in 5 gallon pails (volumes approximate per container)

BENEFITS OF USING

- Excellent adhesion to a variety of substrates
- Excellent low temperature flexibility
- Excellent weathering and UV Stability
- Excellent shelf life
- Good resistance to dirt pickup
- Excellent flexibility
- Easy to use one component product
- Meets Federal VOC requirements
- Resists mildew and fungi growth
- Good resistance to Alkalis and acids

TYPICAL PROPERTIES: (LIQUID FORM)

| PROPERTY | TEST METHOD | RESULT |
|----------------|---|-------------------------------|
| Density | ASTM D1475 U.S. standard weight per gallon cup at 75°F and 50% R.H. | Mean= 10.5#/gallon |
| Particle size | ASTM D1218 | <38 microns or hegman 4-5 |
| VOC | EPA Method 24 | 3.26#/gallon |
| Heat stability | 10 days at 120°F then re-evaluated | Material stability maintained |
| Shelf life | Closed container at 65°F | One year shelf life |
| Flash Point | ASTM D3278 seta flash closed cup apparatus | 105°F |

UNDERWRITERS LABORATORIES, INC., TESTED AND CERTIFIED FOR CLASS A U.L. CERTIFICATION TESTING DATA AVAILABLE UPON REQUEST

TYPICAL PROPERTIES: (CURED FILM)

| PROPERTY | TEST METHOD | RESULTS |
|------------------------|--|--|
| Hardness | ASTM D2240 shore A @ 75°F 50% R.H. Barcol hardness tester model 3061 | 50-60 |
| Accelerated weathering | ASTM G53 (1000 hours QUV accelerated weather tester UV-B lamps no. QES-40/280-315 nanometers (12 hr. QUV @ 60°C and 12 hr. con @ 50°C) | Excellent with no apparent degradation |
| Tensile strength | ASTM D412 @ 75°F and 50% R.H. Test is result of medium value (for 3) | 1000 psi |
| Elongation | ASTM D412 @ 75°F and 50% R.H. | 500% minimum |
| Reflectivity | ASTM E97 | 85% (white) |
| Water absorption | | 0.04% |
| Vapor transmission | ASTM E96 | 0.025 perms |
| Cure time | @70% R.H./70°F | 24-48 hours |

LIMITATIONS

- * Allow material to cure (24 hours) before exposure to rain or dew. Do not apply a second coat until the first coat is dry.
- * Close all sources of air intake from roof into building to prevent solvent odor transfer into building. Do not use indoors.
- * Product cures from solvent evaporation- do not apply thicker than recommended. Too thick of an application can effect insulation boards such as EPS.
- * Read the SDS before using this product.
- * Product is not resistant to solvent exposure.
- * Physical properties are typical values and not specifications. Please see reverse side for limitations of our liability and warranty.
- * Too thick of an application may cause some roofing systems such as “not fully adhered EPDM” to rumple and exhibit some substrate waviness after the application. This waviness will diminish with time, although it may not completely disappear. However, this will not diminish the performance of the substrate.

MIXING AND APPLICATION INSTRUCTIONS

1) **STORAGE:** Store product in an area so as to bring the material to normal room temperature before using. Continuous storage should be between 60 and 80 degree F.

2) **MIXING:** Mix the material before use as needed to provide a uniform mixture. Mix with slow speed equipment to minimize air being whipped into product.

3) **SURFACE PREPARATION:** Make certain that the substrate where the product is to be applied is clean, sound and free of all laitance, dirt, dust, oil, grease, water, dew or foreign contaminants. Power washing will be an effective preparation method for most substrates. Wire brush or abrasive blast all loose and scaling rust from metal surfaces. When topcoating EPDM or seamed roofs, make sure all seams are secure. Precautions should be exercised when coating surfaces with insulation boards such as EPS to determine that the coating will not affect the underlying insulation. When the type of insulation board is unknown, a suitable test patch can be applied to determine suitability. Surface must be dry before application.

4) **ENVIRONMENTAL CONDITIONS:** Do not apply material when temperature is below 40°F during the application time or drying period. Apply material when RH is below 90% for best results. Allow for adequate dry times between

coats and before inclement weather or rain. Higher humidity or lower temperatures will slow the dry time.

5) **APPLICATION:** First, mask off the area where TEXAS-JACK™ RG is to be installed. Then pour/spread onto masked off area. Next, firmly press down on the material with a PHENOLIC CORE roller and spread the material evenly on the surface. Pour only enough material at one time that allows for rolling the material before it becomes tack free. Firm application pressure applied on the phenolic core roller will provide the texture and assure that the material is not being applied too thick. Be sure to apply this product at the specified coverage rate or recommended mil thickness. Some adhesives on existing structures (used to bond the rubber sheets to the deck/structures) may degrade, or are of a poor quality and may not re-bond when the swelling has recovered. Should this occur, you may need to re-bond the sheet rubber with quality adhesives. As we have no control over the type of adhesives used on existing structures, we cannot be held responsible for such occurrences. Apply one gallon per 17.5 square feet per coat (one coat recommended). Always check the substrate for foreign contamination and water before coating. NOTE: If applying over porous substrates, such as concrete but not limited to only concrete, always apply a test patch to determine suitability concerning out-gassing, which could result in pin-holing in both the first coat and subsequent coats as well as potential blisters from the out-gassing.

6) **REOPEN SERVICE TIME:** Take notice of the full cure time and do not open the area to abusive use before the full characteristics of the coating is achieved. Apply when weather permits 24 hours of rain free curing.

7) **MAINTENANCE:** Provide for routine maintenance of your roof to assure years of trouble free performance.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own

*tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.***